

Steelworkers) (collectively, “domestic interested parties”), within the deadline specified in 19 CFR 351.218(d)(1)(i). The domestic interested parties claimed interested party status under sections 771(9)(C) and (D) of the Act, as a domestic producer of stainless steel plate in coils in the United States and a certified union representing workers in the domestic industry producing stainless steel plate in coils in the United States.

The Department received an adequate substantive response collectively from the domestic interested parties within the 30-day deadline specified in 19 CFR 351.218(d)(3)(i). However, the Department did not receive a substantive response from any government or respondent interested party to this proceeding. As a result, pursuant to section 751(c)(3)(B) of the Act and 19 CFR 351.218(e)(1)(ii)(C)(2), the Department conducted an expedited review of the CVD order.

Scope of the Order

The merchandise subject to the CVD order consists of stainless steel plate in coils. Stainless steel is an alloy steel containing, by weight, 1.2 percent or less of carbon and 10.5 percent or more of chromium, with or without other elements. The subject plate products are flat-rolled products, 254 mm or over in width and 4.75 mm or more in thickness, in coils, and annealed or otherwise heat treated and pickled or otherwise descaled. The subject plate may also be further processed (*e.g.*, cold-rolled, polished, *etc.*) provided that it maintains the specified dimensions of plate following such processing.

Excluded from the scope of the order are the following: (1) Plate not in coils, (2) plate that is not annealed or otherwise heat treated and pickled or otherwise descaled, (3) sheet and strip, and (4) flat bars. The merchandise subject to the order is currently classifiable in the Harmonized Tariff Schedule of the United States (“HTSUS”) at subheadings: 7219.11.00.30, 7219.11.00.60, 7219.12.00.05, 7219.12.00.20, 7219.12.00.25, 7219.12.00.50, 7219.12.00.55, 7219.12.00.65, 7219.12.00.70, 7219.12.00.80, 7219.31.00.10, 7219.90.00.10, 7219.90.00.20, 7219.90.00.25, 7219.90.00.60, 7219.90.00.80, 7220.11.00.00, 7220.20.10.10, 7220.20.10.15, 7220.20.10.60, 7220.20.10.80, 7220.20.60.05, 7220.20.60.10, 7220.20.60.15, 7220.20.60.60, 7220.20.60.80, 7220.90.00.10, 7220.90.00.15, 7220.90.00.60, and 7220.90.00.80. Although the HTSUS subheadings are

provided for convenience and customs purposes, the written description of the scope of the order is dispositive.

Analysis of Comments Received

All issues raised in this review are addressed in the Issues and Decision Memorandum (“Decision Memorandum”) from Susan H. Kuhbach, Acting Deputy Assistant Secretary for Antidumping and Countervailing Duty Operations, to Ronald K. Lorentzen, Deputy Assistant Secretary for Import Administration, dated September 30, 2010, which is hereby adopted by this notice. Parties can find a complete discussion of all issues raised in this review and the corresponding recommendations in this public memorandum which is on file in the Central Records Unit, located in room 7046 of the main Commerce building. The issues include the likelihood of continuation or recurrence of a countervailable subsidy, the net countervailable subsidy likely to prevail, and the nature of the subsidy. In addition, a complete version of the Decision Memorandum can be accessed directly on the Web at <http://ia.ita.doc.gov/frn>. The paper copy and electronic version of the Decision Memorandum are identical in content.

Final Results of Review

The Department determines that revocation of the CVD order would be likely to lead to continuation or recurrence of a countervailable subsidy at the following weighted-average percentage rates:

Manufacturers/exporters/ producers	Weighted- average subsidy rate (percent)
Columbus Stainless	3.95
All Others	3.95

Notification Regarding Administrative Protective Order

This notice serves as the only reminder to parties subject to administrative protective order (“APO”) of their responsibility concerning the return or destruction of proprietary information disclosed under APO in accordance with 19 CFR 351.305. Timely notification of return/destruction of APO materials or conversion to judicial protective order is hereby requested. Failure to comply with the regulations and the terms of an APO is a sanctionable violation.

We are issuing and publishing the results and notice in accordance with sections 751(c), 752, and 777(i)(1) of the Act.

Dated: September 30, 2010.

Ronald K. Lorentzen,

Deputy Assistant Secretary for Import Administration.

[FR Doc. 2010-25305 Filed 10-6-10; 8:45 am]

BILLING CODE 3510-DS-P

DEPARTMENT OF COMMERCE

International Trade Administration

[A-428-825, A-588-845, A-580-834, A-583-831]

Certain Stainless Steel Sheet and Strip in Coils From Germany, Japan, the Republic of Korea, and Taiwan: Final Results of the Expedited Second Sunset Reviews of the Antidumping Duty Orders

AGENCY: Import Administration, International Trade Administration, Department of Commerce.

SUMMARY: On June 2, 2010, the Department of Commerce (the Department) initiated second sunset reviews of the antidumping duty orders on certain stainless steel sheet and strip in coils from Germany, Italy, Japan, the Republic of Korea (Korea), Mexico, and Taiwan, pursuant to section 751(c) of the Tariff Act of 1930, as amended (the Act). The Department has conducted expedited (120-day) sunset reviews for the Germany, Japan, Korea, and Taiwan antidumping duty orders pursuant to 19 CFR 351.218(e)(1)(ii)(C)(2).¹ As a result of these sunset reviews, the Department finds that revocation of the antidumping duty orders would be likely to lead to continuation or recurrence of dumping.

FOR FURTHER INFORMATION CONTACT: David Cordell or Angelica Mendoza, AD/CVD Operations, Office 7, Import Administration, International Trade Administration, U.S. Department of Commerce, 14th Street and Constitution Avenue, NW., Washington, DC 20230; telephone: (202) 482-0408, or (202) 482-3019, respectively.

SUPPLEMENTARY INFORMATION

Background

On June 2, 2010, the Department published the notice of initiation of the second sunset reviews of the antidumping duty orders on certain stainless steel sheet and strip in coils from Japan, Germany, Italy, Korea, Taiwan, and Mexico, pursuant to section 751(c) of the Act. *See Initiation of Five-Year (“Sunset”) Review*, 75 FR

¹ With respect to the antidumping duty orders on certain stainless steel sheet and strip in coils from Mexico and Italy, the Department is conducting full sunset reviews.

30777 (June 2, 2010) (*Notice of Initiation*).

The Department received a notice of intent to participate from the AK Steel Corporation; Allegheny Ludlum Corporation; North American Stainless; the United Steel, Paper and Forestry, Rubber, Manufacturing, Energy, Allied Industrial Service Workers International Union; United Auto Workers Local 3303; and United Auto Workers Local 4104 (collectively, "petitioners" or "domestic interested parties") within the deadline specified in 19 CFR 351.218(d)(1)(i). The petitioners claimed domestic interested party status under sections 771(9)(C) and (D) of the Act stating that they are either producers in the United States of a domestic like product or certified unions which are representative of an industry engaged in the manufacture, production, or wholesale in the United States of a domestic like product.

The Department received adequate substantive responses to the *Notice of Initiation* from the domestic interested parties within the 30-day deadline specified in 19 CFR 351.218(d)(3)(i). We received no substantive responses from respondent interested parties with respect to the antidumping duty orders on certain stainless steel sheet and strip in coils from Germany, Japan, Korea and Taiwan. As a result, pursuant to section 751(c)(3)(B) of the Act and 19 CFR 351.218(e)(1)(ii)(C)(2), the Department conducted expedited (120-day) sunset reviews of the antidumping duty orders on certain stainless steel sheet and strip in coils from Germany, Japan, Korea, and Taiwan.

Scope of the Orders

For purposes of the orders, the products covered are certain stainless steel sheet and strip in coils. Stainless steel is an alloy steel containing, by weight, 1.2 percent or less of carbon and 10.5 percent or more of chromium, with or without other elements. The subject sheet and strip is a flat-rolled product in coils that is greater than 9.5 mm in width and less than 4.75 mm in thickness, and that is annealed or otherwise heat treated and pickled or otherwise descaled. The subject sheet and strip may also be further processed (e.g., cold-rolled, polished, aluminized, coated, etc.) provided that it maintains the specific dimensions of sheet and strip following such processing. The merchandise subject to the orders is currently classified in the Harmonized Tariff Schedule of the United States (HTS) at subheadings: 7219.13.00.31, 7219.13.00.51, 7219.13.00.71, 7219.13.00.81, 7219.14.00.30, 7219.14.00.65, 7219.14.00.90,

7219.32.00.05, 7219.32.00.20, 7219.32.00.25, 7219.32.00.35, 7219.32.00.36, 7219.32.00.38, 7219.32.00.42, 7219.32.00.44, 7219.33.00.05, 7219.33.00.20, 7219.33.00.25, 7219.33.00.35, 7219.33.00.36, 7219.33.00.38, 7219.33.00.42, 7219.33.00.44, 7219.34.00.05, 7219.34.00.20, 7219.34.00.25, 7219.34.00.30, 7219.34.00.35, 7219.35.00.05, 7219.35.00.15, 7219.35.00.30, 7219.35.00.35, 7219.90.00.10, 7219.90.00.20, 7219.90.00.25, 7219.90.00.60, 7219.90.00.80, 7220.12.10.00, 7220.12.50.00, 7220.20.10.10, 7220.20.10.15, 7220.20.10.60, 7220.20.10.80, 7220.20.60.05, 7220.20.60.10, 7220.20.60.15, 7220.20.60.60, 7220.20.60.80, 7220.20.70.05, 7220.20.70.10, 7220.20.70.15, 7220.20.70.60, 7220.20.70.80, 7220.20.80.00, 7220.20.90.30, 7220.20.90.60, 7220.90.00.10, 7220.90.00.15, 7220.90.00.60, 7220.90.00.80.

Although the HTS subheadings are provided for convenience and customs purposes, the Department's written description of the merchandise subject to the orders is dispositive. Excluded from the scope of the orders are the following: (1) Sheet and strip that is not annealed or otherwise heat treated and pickled or otherwise descaled; (2) sheet and strip that is cut to length, (3) plate (i.e., flat-rolled stainless steel products of a thickness of 4.75 mm or more), (4) flat wire (i.e., cold-rolled sections, with a prepared edge, rectangular in shape, of a width of not more than 9.5 mm, and (5) razor blade steel. Razor blade steel is a flat-rolled product of stainless steel, not further worked than cold-rolled (cold-reduced), in coils, of a width of not more than 23 mm and a thickness of 0.266 mm or less, containing, by weight, 12.5 to 14.5 percent chromium, and certified at the time of entry to be used in the manufacture of razor blades. See Chapter 72 of the HTS, "Additional U.S. Note" 1(d). Flapper valve steel is also excluded from the scope of the order. This product is defined as stainless steel strip in coils containing, by weight, between 0.37 and 0.43 percent carbon, between 1.15 and 1.35 percent molybdenum, and between 0.20 and 0.80 percent manganese. This steel also contains, by weight, phosphorus of 0.025 percent or less, silicon of between 0.20 and 0.50 percent, and sulfur of 0.020 percent or less. The product is manufactured by means of vacuum arc remelting, with inclusion controls for sulphide of no more than 0.04 percent and for oxide of no more than 0.05

percent. Flapper valve steel has a tensile strength of between 210 and 300 ksi, yield strength of between 170 and 270 ksi, plus or minus 8 ksi, and a hardness (Hv) of between 460 and 590. Flapper valve steel is most commonly used to produce specialty flapper valves in compressors. Also excluded is a product referred to as suspension foil, a specialty steel product used in the manufacture of suspension assemblies for computer disk drives. Suspension foil is described as 302/304 grade or 202 grade stainless steel of a thickness between 14 and 127 microns, with a thickness tolerance of plus-or-minus 2.01 microns, and surface glossiness of 200 to 700 percent Gs. Suspension foil must be supplied in coil widths of not more than 407 mm, and with a mass of 225 kg or less. Roll marks may only be visible on one side, with no scratches of measurable depth. The material must exhibit residual stresses of 2 mm maximum deflection, and flatness of 1.6 mm over 685 mm length. Certain stainless steel foil for automotive catalytic converters is also excluded from the scope of the orders. This stainless steel strip in coils is a specialty foil with a thickness of between 20 and 110 microns used to produce a metallic substrate with a honeycomb structure for use in automotive catalytic converters. The steel contains, by weight, carbon of no more than 0.030 percent, silicon of no more than 1.0 percent, manganese of no more than 1.0 percent, chromium of between 19 and 22 percent, aluminum of no less than 5.0 percent, phosphorus of no more than 0.045 percent, sulfur of no more than 0.03 percent, lanthanum of less than 0.002 or greater than 0.05 percent, and total rare earth elements of more than 0.06 percent, with the balance iron. Permanent magnet iron-chromium-cobalt alloy stainless strip is also excluded from the scope of the orders. This ductile stainless steel strip contains, by weight, 26 to 30 percent chromium, and 7 to 10 percent cobalt, with the remainder of iron, in widths 228.6 mm or less, and a thickness between 0.127 and 1.270 mm. It exhibits magnetic remanence between 9,000 and 12,000 gauss, and a coercivity of between 50 and 300 oersteds. This product is most commonly used in electronic sensors and is currently available under proprietary trade names such as "Arnokrome III."²

Certain electrical resistance alloy steel is also excluded from the scope of the orders. This product is defined as a non-magnetic stainless steel manufactured to

² "Arnokrome III" is a trademark of the Arnold Engineering Company.

American Society of Testing and Materials (ASTM) specification B344 and containing, by weight, 36 percent nickel, 18 percent chromium, and 46 percent iron, and is most notable for its resistance to high temperature corrosion. It has a melting point of 1390 degrees Celsius and displays a creep rupture limit of 4 kilograms per square millimeter at 1000 degrees Celsius. This steel is most commonly used in the production of heating ribbons for circuit breakers and industrial furnaces, and in rheostats for railway locomotives. The product is currently available under proprietary trade names such as "Gilphy 36."³

Certain martensitic precipitation-hardenable stainless steel is also excluded from the scope of the orders. This high-strength, ductile stainless steel product is designated under the Unified Numbering System (UNS) as S45500-grade steel, and contains, by weight, 11 to 13 percent chromium, and 7 to 10 percent nickel. Carbon, manganese, silicon and molybdenum each comprise, by weight, 0.05 percent or less, with phosphorus and sulfur each comprising, by weight, 0.03 percent or less. This steel has copper, niobium, and titanium added to achieve aging, and will exhibit yield strengths as high as 1700 Mpa and ultimate tensile strengths as high as 1750 Mpa after aging, with elongation percentages of 3 percent or less in 50 mm. It is generally provided in thicknesses between 0.635 and 0.787 mm, and in widths of 25.4 mm. This product is most commonly used in the manufacture of television tubes and is currently available under proprietary trade names such as "Durphynox 17."⁴

Finally, three specialty stainless steels typically used in certain industrial blades and surgical and medical instruments are also excluded from the scope of the orders. These include stainless steel strip in coils used in the production of textile cutting tools (e.g., carpet knives).⁵ This steel is similar to AISI grade 420 but containing, by weight, 0.5 to 0.7 percent of molybdenum. The steel also contains, by weight, carbon of between 1.0 and 1.1 percent, sulfur of 0.020 percent or less, and includes between 0.20 and 0.30 percent copper and between 0.20 and 0.50 percent cobalt. This steel is sold under proprietary names such as "GIN4 Mo." The second excluded stainless steel strip in coils is similar to AISI 420-J2 and contains, by weight,

carbon of between 0.62 and 0.70 percent, silicon of between 0.20 and 0.50 percent, manganese of between 0.45 and 0.80 percent, phosphorus of no more than 0.025 percent and sulfur of no more than 0.020 percent. This steel has a carbide density on average of 100 carbide particles per 100 square microns. An example of this product is "GIN5" steel. The third specialty steel has a chemical composition similar to AISI 420 F, with carbon of between 0.37 and 0.43 percent, molybdenum of between 1.15 and 1.35 percent, but lower manganese of between 0.20 and 0.80 percent, phosphorus of no more than 0.025 percent, silicon of between 0.20 and 0.50 percent, and sulfur of no more than 0.020 percent. This product is supplied with a hardness of more than Hv 500 guaranteed after customer processing, and is supplied as, for example, "GIN6."⁶ Also excluded from the orders is a permanent magnet iron-chromium-cobalt stainless steel strip containing, by weight, 13 percent chromium, 6 percent cobalt, 71 percent iron, 6 percent nickel and 4 percent molybdenum. The product is supplied in widths up to 1.27 cm (12.7 mm), inclusive, with a thickness between 45 and 75 microns, inclusive. This product exhibits magnetic remanence between 400 and 780 nWb, and coercivity of between 60 and 100 oersteds. This product is currently supplied under the trade name "SemiVac 90."

Analysis of Comments Received

All issues raised in these sunset reviews are addressed in the "Issues and Decision Memorandum for the Final Results of Expedited Second Sunset Reviews of the Antidumping Duty Orders on Certain Stainless Steel Sheet and Strip in Coils from Germany, Japan, the Republic of Korea, and Taiwan" from Susan H. Kuhbach, Acting Deputy Assistant Secretary for Antidumping and Countervailing Duty Operations, to Ronald K. Lorentzen, Deputy Assistant Secretary for Import Administration (Decision Memo), which is hereby adopted by, and issued concurrently with, this notice. The issues discussed in the Decision Memo are the likelihood of continuation or recurrence of dumping and the magnitude of the margins likely to prevail if the orders were revoked. Parties can find a complete discussion of all issues raised in these reviews and the corresponding recommendations in this public memorandum which is on file in the Central Records Unit, room 7046 of the main Department building. In addition,

a complete version of the Decision Memo can be accessed directly on the Web at <http://ia.ita.doc.gov/frn>. The paper copy and electronic version of the Decision Memo are identical in content.

Final Results of Reviews

We determine that revocation of the antidumping duty orders on certain stainless steel sheet and strip in coils from Germany, Japan, Korea, and Taiwan would be likely to lead to continuation or recurrence of dumping at the following weighted-average percentage margins:

Manufacturers/exporters/producers	Weighted-average margin (percent)
Germany:	
TKN	13.48.
All-Others Rate	13.48.
Japan:	
Kawasaki Steel Corporation/JFE Steel Corporation	40.18.
Nippon Steel Corporation	57.87.
Nisshin Steel Co., Ltd.	57.87.
Nippon Yakin Kogyo	57.87.
Nippon Metal Industries	57.87.
All-Others Rate	40.18.
Korea:	
POSCO	2.49.
Taihan	58.79.
Daiyang (DMC)	5.44.
All-Others Rate	2.49.
Taiwan:	
Tung Mung/Ta Chen	15.40.
Tung Mung	Excluded.
YUSCO/Ta Chen	36.44.
YUSCO	21.10.
All-Others Rate	12.61.

Notification to Interested Parties

This notice also serves as the only reminder to parties subject to administrative protective orders (APO) of their responsibility concerning the return or destruction of proprietary information disclosed under APO in accordance with 19 CFR 351.305. Timely notification of the return or destruction of APO materials or conversion to judicial protective orders is hereby requested. Failure to comply with the regulations and terms of an APO is a violation which is subject to sanction.

We are issuing and publishing the results and notice in accordance with sections 751(c), 752(c), and 777(i)(1) of the Act.

Dated: September 30, 2010.

Ronald K. Lorentzen,
Deputy Assistant Secretary for Import Administration.

[FR Doc. 2010-25299 Filed 10-6-10; 8:45 am]

BILLING CODE 3510-DS-P

³ "Gilphy 36" is a trademark of Imphy, S.A.

⁴ "Durphynox 17" is a trademark of Imphy, S.A.

⁵ This list of uses is illustrative and provided for descriptive purposes only.

⁶ "GIN4 Mo," "GIN5" and "GIN6" are the proprietary grades of Hitachi Metals America, Ltd.